



Korepox H.B. EH6270H-MIO (Two-Component)

Product Description	A high-build, micaceous iron oxide (MIO) pigmented polyamide cured epoxy paint providing a hard and tough film with excellent resistance to abrasion and impact. It provides good resistance to water and excellent anti-corrosive property.
Recommended Use	As a high-build primer or intermediate coat for use on general steel structures. For structures exposed to outdoor, urethane topcoat is recommended to use.

Physical Properties

Finish and Color Flat. Metallic Grey(MIO)

Drying Time	Substrate temperature	5 °C / 41 °F	20 °C / 68 °F	30 °C / 86 °F
	Set to touch	18 h	4 h	3 h
	Dry through	72 h	24 h	20 h

* The actual drying time is subject to the film thickness, ventilation, humidity etc., and drying time under other temperature conditions should be checked and informed by KCC.

Solids by Volume Approx. 70 % (Determined by ISO 3233)

Theoretical Spreading Rate 7 m²/L in 100 μm dry film thickness on a smooth surface.

Specific Gravity Approx. 1.3 ~ 1.45 for Mixture of Base and Curing agent.

Flash Point Base (EH6270H-A) : 26 °C / 79 °F (Closed cup)
Curing Agent (EH6270H-B) : 49 °C / 120 °F (Closed cup)

Application Details

Surface Preparation Remove any oil, grease, dirt and any other contaminants from the surface before painting by proper method such as solvent cleaning and fresh water washing, etc.
* Steel : Blast cleaning to Sa2.5 or Power tool cleaning to St3, etc.

Application Conditions Apply only where application and curing can proceed at temperatures above 5 °C/41 °F. The surface should be completely cleaned and dried. Do not apply when relative humidity is above 85 %. The surface temperatures should be at least 2.7 °C (5 °F) above dew point to prevent condensation. In confined areas, ventilate with clean air during application to assist solvent evaporation.

Mixing Base (Part A) : Curing Agent (Part B) = 4 : 1 (by volume)
Mix thoroughly together prior to application in the proportions with power agitator as delivered.

Pot Life 4 h at 20 °C / 68 °F

Preceding coat Galvany IZ180N or according to specification.
When apply over inorganic zinc, a mist coat is required to reduce the bubbling.

Thinning Thinner No. 024, 024M or Other thinner approved by KCC
Do not dilute components separately, only the mixture.

Disclaimer : The information in this data sheet is believed to the best of our knowledge based on laboratory test and practical experience. However, there are many factors affecting the performance of product and the product quality itself, so we are not able to guarantee without the confirmation of the purpose of using the product from us in writing. We reserve the right to change the data without notice and you should check that this data sheet is current prior to using the product.



KCC Corporation

Korepox H.B. EH6270H-MIO (Two-Component)

Application Method	Spray (Airless or Air), Roller or Brush application. For airless spray application ; Nozzle orifice : 432 μm ~ 635 μm (0.017" ~ 0.025") Output pressure : 11.7 MPa ~ 15.2MPa Fan : 40 ° ~ 60 ° (Airless spray data are indicative and subject to adjustment)
Typical Film Thickness	100 μm dry. May be specified in another film thickness than indicated depending on purpose and area of use.
Recoating Interval	At 20°C / 68°F, Minimum : 18 h Maximum : 30day Prior to overcoating, remove the oil, salt, chalking material and any other contaminants on aged coating film completely by proper cleaning method such as solvent cleaning and/or fresh water washing.
Subsequent Coat	Korethan Topcoat UT6581 or according to specification.
Shelf Life	12 months
Heat Resistance	Continuous : 93 °C / 200 °F (Non-immersion service) Non-continuous : 121 °C / 250 °F (Non-immersion service)
Standard Packing Unit	16 L (EH6270H-A : 12.8 L, EH6270H-B : 3.2 L)
Remarks	Protect skin and eyes from direct contact with liquid paint, and avoid prolonged breathing of solvent vapors. Use with adequate ventilation. Respiratory protection is recommended during application in confined spaces or stagnant air.
Issued	April 2013, Rev.01